



SORA silico EPC

SORA silico EPC is clay coated craft – 1 side.

Parameter	Standard	36	40	43	45	47	50	55	60	65	70	75	80	90	105	125	Tolerance
Grammage [g/m ²]	ISO 536	36	40	43	45	47	50	55	60	65	70	75	80	90	105	125	± 2
Thickness [µm]	ISO 534	42	45	48	50	53	56	62	67	71	78	83	90	101	108	129	± 4
Smoot. Bendtsen – coated side [ml/min]	ISO 8791-2	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	± 20
Abs. humidity [%]	DIN EN 20287	4.0	4.0	4.0	4.0	4.0	4.0	4.0	4.0	4.0	4.0	4.0	4.0	4.0	4.0	4.0	± 0.5
D65 Brightness [%]	ISO 2470-2 (D65/10°)	80	80	80	80	80	80	80	80	80	80	80	80	80	80	80	min
Cobb 120 (castor oil) [g/m ² /120s]	DIN EN 20535	2.5	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2	max

Given values can be used as guide values only and can be changed without prior notice.
For a valid specification, please refer to the one most recently published on the website www.goricane.si.
Information on the supplies of FSC® and PEFC™ certified products are available in the Sales department.

