



Paper Specification  
TS – 16.07.2019

# SORA silico PVA

SORA silico PVA is clay coated craft – 2 sides.

Parameter	Standard	90	Tolerance
Grammage [g/m <sup>2</sup> ]	ISO 536	90	± 2
Thickness [µm]	ISO 534	90	± 4
Smoot. Bendtsen – coated side [ml/min]	ISO 8791-2	50	± 20
Abs. humidity [%]	DIN EN 20287	3.8	± 0.5
D65 Brightness [%]	ISO 2470-2 (D65/10°)	80	min
Cobb 120 (castor oil) [g/m <sup>2</sup> / 120s]	DIN EN 20535	3.5	max

Given values can be used as guide values only and can be changed without prior notice.  
For a valid specification, please refer to the one most recently published on the website [www.goricane.si](http://www.goricane.si).  
Information on the supplies of FSC® and PEFC™ certified products are available in the Sales department.

