



Paper Specification
TS – 12.08.2019

SORA medico opaque

SORA medico opaque is a woodfree lightweight uncoated paper with high opacity.

Parameter	Standard	37	40	45	50	60	Tolerance
Grammage [g/m ²]	ISO 536	37	40	45	50	60	± 2
Thickness [µm]	ISO 534	47	50	56	61	74	± 4
Smoot. Bendtsen [ml/min]	ISO 8791-2	90	90	90	90	90	± 40
Rel. humidity [%]	DIN 53118	4.5	47.5	47.5	47.5	47.5	± 7.5
CIE Whiteness [%]	ISO 11475 (D65/10°)	117	117	117	117	117	± 4
Opacity [%]	ISO 2471	80	83	85	88	91	± 2

Given values can be used as guide values only and can be changed without prior notice.
For a valid specification, please refer to the one most recently published on the website www.goricane.si.
Information on the supplies of FSC® and PEFC™ certified products are available in the Sales department.

