



Paper Specification
TS – 12. 11. 2020

SORA barrier 2GO 8 WS-H

SORA barrier 2GO 8 WS-H is two-side oil and grease resistant paper with high wet- strength properties.

Parameter	Standard	50	55	60	Tolerance
Grammage [g/m ²]	ISO 536	50	55	60	± 2
Thickness [µm]	ISO 534	61	67	71	± 4
Smoot, Bendtsen [ml/min]	ISO 8791- 2	200	200	200	
Tensile strength (MD) [kN/m]	DIN EN ISO 1924	4,8	5,0	5,5	
Tensile strength (CD) [kN/m]	DIN EN ISO 1924	3,0	3,3	3,6	
Burst [kPa]	ISO 2758	200	240	280	
Wet strength [%]	DIN 53112	20	20	20	min
Cobb ₆₀ [gH ₂ O/m ²]	ISO 535	20	20	20	± 5
ISO Brightness [%]	ISO 2470-2 (D65 / 10°)	85	85	85	
KIT test	T559	8	8	8	± 1
Moisture content [%]	ISO 287	5,5	5,5	5,5	

*Given values can be used as guide values only and can be changed without prior notice.
For a valid specification, please refer to the one most recently published on the website www.goricane.si.
Information on the supplies of FSC® and PEFC™ certified products are available in the Sales department.*

