



Paper Specification
TS – 12. 11. 2020

SORA barrier 2GO 5 WS-M

SORA barrier 2GO 5 WS-M is two-side oil and grease resistant paper with medium wet-strength properties.

Parameter	Standard	30	36	38	40	45	50	55	Tolerance
Grammage [g/m ²]	ISO 536	30	36	38	40	45	50	55	± 2
Thickness [µm]	ISO 534	40	45	48	50	56	61	67	± 4
Smoot, Bendtsen [ml/min]	ISO 8791-2	200	200	200	200	200	200	200	
Tensile strength (MD) [kN/m]	DIN EN ISO 1924	3,0	3,3	3,5	3,8	4,5	4,8	5,0	
Tensile strength (CD) [kN/m]	DIN EN ISO 1924	1,8	2,0	2,1	2,3	2,7	3,0	3,3	
Burst [kPa]	ISO 2758	120	140	150	160	180	200	240	
Wet strength [%]	DIN 53112	12	12	12	12	12	12	12	min
Cobb ₆₀ [gH ₂ O/m ²]	ISO 535	20	20	20	20	20	20	20	± 5
ISO Brightness [%]	ISO 2470-2 (D65/10°)	85	85	85	85	85	85	85	
KIT test	T559	5	5	5	5	5	5	5	± 1
Moisture content [%]	ISO 287	5,5	5,5	5,5	5,5	5,5	5,5	5,5	

Given values can be used as guide values only and can be changed without prior notice.
For a valid specification, please refer to the one most recently published on the website www.goricane.si.
Information on the supplies of FSC® and PEFC™ certified products are available in the Sales department.

