


SORA press

SORA press is a woodfree uncoated graphic paper.



press

TS – 12. 10. 2021

	STANDARD	60	65	70	75	80	90	100	110	120	Tolerance
GRAMMAGE [g/m ²]	ISO 536	60	65	70	75	80	90	100	110	120	± 2
SPEC. VOLUME [cm ³ /g]	ISO 534	1.16	1.16	1.14	1.14	1.13	1.1	1.1	1.08	1.08	± 0.07
SMOOT. BENDTSEN [ml/min]	ISO 8791-2	120	120	120	120	120	120	120	120	120	± 40
RELATIVE HUMIDITY [%]	DIN 53118	47.5	47.5	47.5	47.5	47.5	47.5	47.5	47.5	47.5	± 7.5
CIE WHITENESS [%]	ISO 11475 (D65/10°)	145	145	145	145	145	145	145	145	145	± 4
OPACITY [%]	ISO 2471	87	89	90	92	93	95	97	98	99	± 2

Given values can be used as guide values only and can be changed without prior notice.
For a valid specification, please refer to the one most recently published on the website www.goricane.si.
Information on the supplies of FSC® and PEFC™ certified products are available in the Sales department.



ISEGA

GORIČANE